



7532

Fiber Glass Fabric

Product Data

STYLE 7532 **US System** **SI Units**

Type of Yarns	Warp Yarn:	ECG 75 1/3	EC9 68 x3
	Fill Yarn:	ECG 75 1/3	EC9 68 x3
Fabric Weight, Dry		7.23 oz/yd ²	245 g/m ²
Weave Style	Plain		

CONSTRUCTION

Nominal Construction	Warp Count:	16/in	6.3/cm
	Fill Count:	14/in	5.5/cm
Fabric Thickness		10.0 mils	0.25 mm
Yarn Breaking Strength	Warp	250 lbf/in	219 daN/5cm
	Filling	200 lbf/in	175 daN/5cm

Markets

Recreational

Applications

Low Pressure Composites

IMPORTANT

All information is believed to be accurate but is given without acceptance of liability. All values have been generated from limited data. The values listed for weight, thickness, and breaking strengths are typical greige values, unless otherwise noted. Users should make their own assessment of the suitability of any product for the purpose required. All sales are made subject to our standard terms of sales which include limitations on liability and other important terms. The fabric style listed may not be available from inventory, and minimum order quantities may apply.

FOR FURTHER INFORMATION, PLEASE CONTACT US



2200 S. Murray Ave.
Anderson, SC 29622
USA
Phone: 864-225-7028
Fax: 864-260-6581

580 North Gilbert St.
Fullerton, CA 92833
USA
Phone: 714-278-0850
Fax: 714-526-2367

3, Avenue Condorcet
69608 Villeurbanne Cedex
France
Phone: 33 4 72 44 40 00
Fax: 33 4 78 89 72 30