



# T.R. Industries

11022 VULCAN ST., PO. BOX 2306  
SOUTH GATE, CALIFORNIA 90280-0893  
PHONE: 582-923-0838 • FAX (562) 861-3475

---

## TR-104 HI-TEMP MOLD RELEASE

### DESCRIPTION:

A firm Mold Release Paste Wax based on the highest quality Refined Carnauba Wax blended with other synthetic high temperature ingredients and petroleum distillates.

### PRODUCT FEATURES:

- ★ Ease of application and removal. May be allowed to stand at length & still polish wipe easily.
- ★ Provides hard film with superior heat & chemical properties.
- ★ Polishes too high gloss with out streaking.
- ★ Reduced wax build-up and styrene accumulation.

### PHYSICAL PROPERTIES:

**DRY-TIME** - 5-10 minutes. @ 72°F. Will vary depending on working temperature.

**MELT POINTS** - 180-210°F

**PENETRATION HARDNESS** - 1 at 25°C  
(Carnauba Wax)

**COLOR** - Light blue tint. Color-coded for identification.

**USES:** As release agent for Polyester/Fiber Glass molding on all FRP tooling, Formica, Metal and other hard surface molds.

- ★ Open mold hand or spray lay-up
- ★ Compression molding
- ★ Resin transfer molding(RTM)
- ★ Vacuum bag

**NOTE:** Check suitability when heat curing or higher temperature molding above 200°F. (94°C)

### APPLICATION:

On new or reconditioned tooling suggest use of our sealer glaze **TR-301** prior to waxing for added release, gloss and mold life. Apply wax with the sponge applicator in a thin even circular motion to the mold surface. Allow to haze dry (approx. 5-10 min.) and polish wipe to gloss finish. For new or reconditioned molds apply minimum of 6 coats of paste wax waiting approx. 30-60 minutes between applications for the wax to harden after your polish wipe. Best results obtained if after final application, mold is allowed to stand over night and a subsequent final coat of wax release applied following day prior to gel-coating. Follow with a coat of wax for the first 2-3 parts released. Then determine how many parts can be effectively produced before rewaxing is required. Will vary depending on mold condition, configuration, type of resin, mold cycles, effective cure of production gel-coat and other factors.

The information contained herein is based on tests considered to be reliable and accurate. Because of the wide variance of associated materials and conditions. however. no warranty is expressed or implied. Each user is encouraged to prepare a test part for his particular application.