

NA 983-085

Low Density Polyethylene Film Extrusion Grade

Melt Index 0.25 Density 0.920

Applications

PETROTHENE NA 983-085 is a low density polyethylene resin designed for heavy duty and shrink film applications produced by blown film extrusion. NA 983-085 exhibits high impact strength and good bubble stability. This product contains medium levels of antiblock additives.

Regulatory Status

NA 983-085 meets the requirements of the Food and Drug Administration, 21 CFR 177.1520. This regulation allows the use of this olefin polymer'...in articles or components of articles intended for use in contact with food.' Specific limitations or conditions of use may apply. Contact your Lyondell sales representative for more information.

Processing Techniques

Specific recommendations for processing NA 983-085 can only be made when the processing conditions, equipment and end use are known. For further suggestions, please contact your Lyondell sales representative.

Typical Properties*

Property	Nominal Value	Units	ASTM Test Method
Melt Index	0.25	g/10 min	D 1238
Density	0.920	g/cc	D 1505
Film**			
Dart Drop Impact Strength, F ₅₀	180	g	D 1709
Tensile Strength, MD (TD)	3,000 (2,800)	psi	D 882
1% Secant Modulus, MD (TD)	30,000 (35,000)	psi	E 111
Elongation, MD (TD)	310 (430)	%	D 882

* These are typical values and are not to be construed as specific product limits.

** Film gauge: 1.25 mils

The information on this document is, to our knowledge, true and accurate. However, since the particular uses and the actual conditions of use of our products are beyond our control, establishing satisfactory performance of our products for the intended application is the customer's sole responsibility. All uses of Equistar products and any written or oral information, suggestions or technical advice from Equistar are without warranty, express or implied, and are not an inducement to use any process or product in conflict with any patent.

Equistar materials are not designed or manufactured for use in implantation in the human body or in contact with internal body fluids or tissues. Equistar makes no representation, promise, express warranty or implied warranty concerning the suitability of these materials for use in implantation in the human body or in contact with internal body tissues or fluids.

More detailed safety and disposal information on our products is contained in the Material Safety Data Sheet (MSDS). All users of our products are urged to retain and use the MSDS. A MSDS is automatically distributed upon purchase/order execution. You may request an advance or replacement copy by calling our MSDS Hotline at (800) 700-0946.

® Equistar and Petrothene are registered trademarks of Equistar Chemicals, LP.

Lyondell Chemical Company
1221 McKinney, Suite 700
P.O. Box 2583
Houston, Texas 77252-2583
(800) 615-8999
<http://www.equistarchem.com>

6723-56/0703

